

Product Data Sheet: NeoPac® E-128

NeoPac® E-128 is a fatty acid modified acrylic polyurethane dispersion for use in decorative paints and wood stains.

Typical properties

Type	Fatty acid modified acrylic-polyurethane dispersion
Appearance	Milky white
Total solids (% w/w)	36.5%
pH (25°)	8.0
viscosity Brookfield (25°C; mPa.s)	< 200
MFT (°C)	5
Density of emulsion (20°C; kg/l)	1.04 g/cm ³

Film properties

- Good flow
- Good open time / wet edge
- Low yellowing
- Good early blocking
- Good water resistance
- No cissing

Recommendation for end-use

- Decorative topcoats and woodstains

Formulating guidelines

- For good film formation use cosolvents e.g. Dowanol DPM

Safety

All relevant data have been brought up-to-date in the Material Safety Data Sheet for NeoPac® E-128.

NeoPac® E-128

Intro Date : July 2008

Rev. Date : March 30,2009

Print date : 30-Mar-09

DSM NeoResins B.V. Sluisweg 12 P.O. Box 123 5140 AC Waalwijk The Netherlands Telephone +31 (0)416 68 99 11 Telefax +31 (0)416 68 99 22 Internet www.dsmneoresins.com

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent. All sales of these products shall be subject to DSM NeoResins' standard conditions of sales.