

Product Data

Somos[®] 9110

Description

DSM's Somos[®] 9110 is a liquid photopolymer that produces robust, functional and accurate parts using stereolithography machines. The material offers superior chemical resistance, a wide processing latitude and excellent tolerance to a broad range of temperatures and humidity during and after the build. Parts created from Somos[®] 9110 exhibit superior fatigue properties, strong memory retention and high quality up-facing and down-facing surfaces. Somos[®] 9110 also offers a good balance of properties between rigidity and functionality. The resulting part properties are ideal for master patterns in rubber molding applications.

Applications

Somos[®] 9110 photopolymer is used in the solid imaging process to build three-dimensional parts. also useful in creating parts for applications where durability and robustness are critical requirements (e.g., automobile components, electronic housings, medical products, large panels and snap-fit parts).

TECHNICAL DATA - LIQUID PROPERTIES	
Appearance	Transparent amber
Viscosity	~230 cps @ 30°C
Density	~1.13 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES		
E _c	8.0 mJ/cm ²	[critical exposure]
D _p	5.2 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	55 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

TECHNICAL DATA					
Mechanical Properties		Somos [®] 9110 UV Postcure		Polypropylene*	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
D638M	Tensile Strength	31 MPa	4.5 ksi	31 - 37.2 MPa	4.5 - 5.4 ksi
D638M	Elongation at Yield	15 - 21%	15 - 21%	7 - 13%	7 - 13%
D638M	Young's Modulus	1,590 MPa	231 ksi	1,138 - 1,551 MPa	165 - 225 ksi
D790M	Flexural Strength	44 MPa	6.4 ksi	41 - 55 MPa	6 - 8 ksi
D790M	Flexural Modulus	1,450 MPa	210 ksi	1,172 - 1,724 MPa	170 - 250 ksi
D2240	Hardness (Shore D)	83	83	N/A	N/A
D256A	Izod Impact (Notched)	55 J/m	1.03 ft-lb/in	21 - 75 J/m	0.4 - 1.4 ft-lb/in
D648-07	Deflection Temperature	50°C	122°F	107 - 121°C	225 - 250°F

*Unfilled polypropylene (Reference: Modern Plastics Encyclopedia, 1997)

DSM Functional Materials
Somos® Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties or merchantability and/or fitness for a particular purpose DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2012 DSM IP ASSETS B.V. All rights reserved.