

# Somos® PerFORM Reflect



**In motorsports – as in automotive, rail and aerospace - speed is key. Getting ready for a race, from design to the track you need to be the fastest. Printing your wind tunnel models with Somos® PerFORM Reflect saves more than 30% post treatment. So, you can get your aerodynamic designs onto your vehicle faster - and be more competitive on the track, road, rail or air.**

In Formula One, typically a car body is printed at 60% of its normal size for simulation purposes and checked with particle imaging velocimetry (PIV) in critical areas. Somos® PerFORM Reflect is a new and unique DSM stereolithography material developed specifically for 3D printing parts for wind tunnel testing with PIV. With this innovation DSM again sets a standard in enabling faster aerodynamic design optimizations - in motorsports and beyond.

Somos® PerFORM Reflect produces strong, stiff, high-temperature resistant composite parts that are ideal for wind tunnel testing. Extensive tests show that the new Somos® PerFORM Reflect reduces post-processing by more than 30% as it eliminates the need for additional PIV coatings. This translates into faster data collection, decreasing overall lead time per design iteration and allowing customers to conduct iterations faster.

Somos® PerFORM Reflect utilizes patented new technology that allows for reducing and even eliminating much of the finishing work required with traditional materials. Based on DSM's industry standard Somos® PerFORM, the new resin demonstrates all the performance attributes that customers rely on such as low viscosity, low settling, fast processing and high stiffness and heat resistance.



## Key Benefits

- Ready-to-use material for PIV wind tunnel testing
- Faster image processing, higher accuracy wind tunnel models
- >30% reduction in post-processing time
- Excellent detail resolution
- Improved surface quality, faster part finishing
- Superior high heat properties

## Applications

- Wind tunnel testing for aerodynamic design optimization
- High-temperature testing
- Electrical casings
- Automotive housings
- Tooling



*Motorsports engine cover vent printed in Somos® PerFORM Reflect*

## Technical Data

Liquid Properties		Optical Properties		
Appearance	Orange	$E_c$	8.4 mJ/cm <sup>2</sup>	[critical exposure]
Viscosity	~1100cP @ 30°C	$D_p$	4.15 mil	[slope of cue-depth vs ln (E) curve]
Density	~1.61 g/cm <sup>3</sup> @ 25°C	$E_{10}$	93.4 mJ/cm <sup>2</sup>	[exposure that gives 0.254 mm (.010 inch) thickness]

Mechanical Properties		UV Postcure		Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
D638-14	Tensile Strength	63.3 MPa	9180	72.4 MPa	10500 psi
D638-14	Tensile Modulus	10135 MPa	1470 ks	9653 MPa	1400 ksi
D638-14	Elongation at Break	0,79%		0,96%	
D638-14	Poisson's Ratio	0,318		0,315	
D790-15e2	Flexural Strength	119 MPa	17300 psi	130 MPa	18800 psi
D790-15e2	Flexural Modulus	8273 MPa	1200 ksi	7722 MPa	1120 ksi
D256-10e1	Izod Impact (Notched)	16.9 J/m	0.316 ft-lbf/in	20.0 J/m	0.375 ft-lbf/in
D2240-15	Hardness (Shore D)	92		94	
D570-98	Water Absorption	0,19%		0,14%	

Thermal/Electric Properties		UV Postcure		Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial	Metric	Imperial
E831-14	C.T.E. -40 - 0°C (-40 - 32°F)	26.3 μm/m°C	14.6 μin/in°F	25.7 μm/m°C	14.3 μin/in°F
E831-14	C.T.E. 0 - 50°C (32 - 122°F)	35.8 μm/m°C	19.9 μin/in°F	31.5 μm/m°C	17.5 μin/in°F
E831-14	C.T.E. 50 - 100°C (122 - 212°F)	88.3 μm/m°C	49.1 μin/in°F	50.5 μm/m°C	28.1 μin/in°F
E831-14	C.T.E. 100 - 150°C (212 - 302°F)	85.8 μm/m°C	47.7 μin/in°F	87.4 μm/m°C	48.5 μin/in°F
D150-18	Dielectric Constant 60 Hz	4,22		4,22	
D150-18	Dielectric Constant 1 kHz	3,96		3,92	
D150-18	Dielectric Constant 1 MHz	3,67		3,65	
D149-09	Dielectric Strength	6.6 kV/mm	675 V/mil	27.5 kV/mm	699 V/mil
E1545-11	Tg via DMA (E'')	70°C	158°F	94°C	201°F
D648-16	HDT @ 0.46 MPa (66 psi)	94.0°C	201°F	276°C	529°F
D150-18	HDT @ 1.81 MPa (264 psi)	76.5°C	170°F	122°C	252°F

### More information

For more information and buying options, please visit [www.dsm.com/additive-manufacturing/](http://www.dsm.com/additive-manufacturing/)

DSM – Bright Science. Brighter Living.™

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information. Somos® is a trademark of DSM.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM. Doc 0009-01