



Product Data Sheet

Somos[®] BioClear

Description

DSM's Somos[®] BioClear produces clear, strong, tough and water-resistant parts. This product is the first in the Somos[®] BioLine portfolio for medical applications and is ISO 10993-5, ISO 10993-10 and USP VI certified.

Applications

Somos[®] BioClear is designed for medical applications that are non-implant and have limited contact with the body, such as dental drill guides and device prototyping.**

TECHNICAL DATA - LIQUID PROPERTIES

Appearance	Optically clear, near colorless
Viscosity	~260 cps @ 30°C
Density	~1.12 g/cm ³ @ 25°C

TECHNICAL DATA - OPTICAL PROPERTIES

E _c	11.5 mJ/cm ²	[critical exposure]
D _p	6.50 mils	[slope of cure-depth vs. ln (E) curve]
E ₁₀	54 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

** The parameters for medical testing are limited. It remains the responsibility of the device manufacturers to determine the usage fit for each particular device.

TECHNICAL DATA			
Mechanical Properties		Somos® BioClear UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Strength at Break	47.1 - 53.6 MPa	6.8 - 7.8 ksi
D638M	Elongation at Break	11 - 20%	11 - 20%
D638M	Elongation at Yield	3%	3%
D638M	Modulus of Elasticity	2,650 - 2,880 MPa	384 - 420 ksi
D790M	Flexural Strength	63.1 - 74.2 MPa	9.2 - 10.8 ksi
D790M	Flexural Modulus	2,040 - 2,370 MPa	296 - 344 ksi
D256A	Izod Impact (Notched)	0.2 - 0.3 J/m	0.4 - 0.6 ft-lb/in
D542	Index of Refraction	1.512 - 1.515	1.512 - 1.515
D1004-09	Graves Tear	150,288 N/m	833 - 858 ft-lb/in
D570-98	Water Absorption	0.35%	0.35%

TECHNICAL DATA			
Thermal/Electrical Properties		Somos® BioClear UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	66 - 67 µm/m°C	37 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	90 - 96 µm/m°C	50 - 53 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	170 - 189 µm/m°C	94 - 105 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	185 - 189 µm/m°C	103 - 105 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.9 - 4.1	3.9 - 4.1
D150-98	Dielectric Constant 1 KHz	3.7 - 3.9	3.7 - 3.9
D150-98	Dielectric Constant 1 MHz	3.4 - 3.5	3.4 - 3.5
D149-97A	Dielectric Strength	15.4 - 16.3 kV/mm	390 - 413 V/mil
E1545-00	Tg	39 - 46°C	102 - 109°F
D648	HDT @ 0.46 MPa (66 psi)	45.9 - 54.5°C	115 - 130°F
D648	HDT @ 1.81 MPa (264 psi)	49.0 - 49.7°C	120°F

DSM Functional Materials Somos® Materials Group

in North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

in Europe

Slachthuisweg 30
3150 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

in China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.
© 2012 DSM IP ASSETS B.V. All rights reserved.